

NEWTECHWOOD CORPORATION

TEST REPORT

SCOPE OF WORK

Interior Wall Panel

REPORT NUMBER

230410119GZU-003

TEST DATE(S)

2023-04-10 ~ 2023-05-19

ISSUE DATE

2023-05-24

[REVISED DATE]

/

PAGES

10



Intertek Testing Services Shenzhen Ltd. Guangzhou Branch



DOCUMENT CONTROL NUMBER

TTRF_Performance_02a

Effective date:2020-12-30

© 2020 INTERTEK

Test Report

Report No.: 230410119GZU-003
Report Date: 2023-05-24

Statement

- 1.This report is invalid without authorized person's signature.
- 2.This report is invalid where any unauthorized modification indicated.
- 3.Don't copy this report in partial (except full copy) without any official approval in written by our company.
- 4.This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Only the Client is authorized to permit copying or distribution of this report and then only in its entirety. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample(s) tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.
- 5.All the tests results give the statement of conformity refer to the decision rule of "Procedure 2 "Accuracy Method" as stated in the IEC Guide 115:2007.



Test Report

Report No.: 230410119GZU-003

Report Date: 2023-05-24

Client Information:

Applicant Name:	NEWTECHWOOD CORPORATION
Address:	19111 Walden Forest Dr. Suite B Humble, Tx 77346, USA
Attn:	/

Product Information:

Product Name	Interior Wall Panel	Sample Description	Good Condition
Model and/or type reference	/	Received Date	2023-04-10
Sample ID.	S230410119GZU.002	Sample Amount	1 BOX
Manufacturer	NEWTECHWOOD CORPORATION		
Address	Wutang Section, 12 Tuo, Daling, Huidong, Huizhou, Guangdong, China		
Test Type	Performance test, samples provided by the applicant		

Test Methods And Standards:

Test Standard	Please refer to the following pages.
Specification Standard	Please refer to the following pages.
Test Conclusion	Please refer to the following pages.

Laboratory information:

Testing Laboratory	Intertek testing services Shenzhen Ltd. Guangzhou Branch
Test location	No. 8, East BaoYing Road, Huangpu District, Guangzhou, China

Report Authorized :

Approved By:

Penny Pan

Penny Pan
Asst. Technical Manager

Checked By:

Jim Liang

Jim Liang
Engineer

Noted: If you have any questions for the report, please contact: lillian.lf.he@intertek.com

Test Report

Report No.: 230410119GZU-003

Report Date: 2023-05-24

Test Items, Method and Results:

1. Test standard:

CDPH/EHLB/Standard Method V1.2, 2017

Standard Method for the Testing and Evaluation of Volatile Organic Chemical Emissions from Indoor Sources using Environmental Chambers Version 1.2 - Emission testing method for California Specification 01350

2. Test method:

With reference to

ASTM D5197-16 Standard Test Method for Determination of Formaldehyde and Other Carbonyl Compounds in Air (Active Sampler Methodology);

ASTM D6196-15e1 Standard Practice for Choosing Sorbents, Sampling Parameters and Thermal Desorption Analytical Conditions for Monitoring Volatile Organic Chemicals in Air;

U.S. EPA. Method TO-17. 1997. Determination of Volatile Organic Compounds in Ambient Air Using Active Sampling Onto Sorbent Tubes;

ISO 16000-9:2006 Indoor air - Part 9: Determination of the emission of volatile organic compounds from building products and furnishing - Emission test chamber method;

ISO 16000-11:2006 Indoor air - Part 11: Determination of the emission of volatile organic compounds from building products and furnishing - Sampling, storage of samples and preparation of test specimens.(ASTM D5197-16, ASTM D6196-15e1, U.S. EPA. Method TO-17. 1997, ISO 16000-11:2006 are not accredited by CNAS.)

3. Test Procedure:

The sample was tested in the emission test chamber. After defined times, chamber air samples were collected. Samples analyzed for individual VOCs and TVOC were collected on sorbent tubes Tenax TA, and were detected by Automatic Thermal Desorption-Gas Chromatography/Mass Spectrometric (ATD-GC/MS). Samples analyzed for aldehydes were collected on DNPH cartridge, and were detected by High Performance Liquid Chromatography (HPLC).

4. Conditioning of the sample until testing date:

23°C±2°C, 50%±5%, 10 days

5. Test condition:

Test chamber	:	0.06	m ³
Exposed sample surface area	:	0.06	m ²
Loading factor	:	1	m ² /m ³
Supply air temperature	:	23±1	°C
Supply air humidity	:	50±5	% R.H
Air exchange rate	:	1.0	h ⁻¹
Area specific flow rate	:	1	m/h
Sampling	:	Tenax TA & DNPH cartridge	

Test Report

Report No.: 230410119GZU-003

Report Date: 2023-05-24

6. Test result:

Table 1 Evaluation for different scenarios

Modeling scenario	Verdict(Pass/Fail)
Standard school classroom (SC)	Pass
Private office (PO)	Pass
Single family residence &	Pass

Remark:

&The single family residence modeling scenario is not yet a requirement and is for informational purposes only.

Table 2 24h, 48h and 96h Chamber Concentration and Emission Factor of Formaldehyde and TVOC

Parameter	CAS No.	Chamber Concentration $\mu\text{g}/\text{m}^3$			Emission Factor $(\mu\text{g}/\text{m}^2\cdot\text{hr})$		
		24h	48h	96h	24h	48h	96h
Formaldehyde [#]	50-00-0	<2	<2	<2	<2	<2	<2
TVOC	/	<10	<10	<10	<10	<10	<10

Table 3 96h Chamber concentration and Emission Factor of all Target VOCs

No.	Compound Name	CAS No.	Chamber Concentration $\mu\text{g}/\text{m}^3$	Emission Factor $(\mu\text{g}/\text{m}^2\cdot\text{hr})$
1	Acetaldehyde [#]	75-07-0	3	3
2	Benzene	71-43-2	<1	<1
3	Carbon disulfide	75-15-0	<2	<2
4	Carbon tetrachloride	56-23-5	<2	<2
5	Chlorobenzene	108-90-7	<2	<2
6	Chloroform	67-66-3	<2	<2
7	Dichlorobenzene (1,4-)	106-46-7	<2	<2
8	Dichloroethylene (1,1)	75-35-4	<2	<2
9	Dimethylformamide (N,N-)	68-12-2	<2	<2
10	Dioxane (1,4-)	123-91-1	<2	<2
11	Epichlorohydrin	106-89-8	<1	<1
12	Ethylbenzene	100-41-4	<2	<2
13	Ethylene glycol	107-21-1	<2	<2
14	Ethylene glycol monoethyl ether	110-80-5	<2	<2
15	Ethylene glycol monoethyl ether acetate	111-15-9	<2	<2
16	Ethylene glycol monomethyl ether	109-86-4	<2	<2
17	Ethylene glycol monoethyl ether acetate	110-49-6	<2	<2
18	Formaldehyde [#]	50-00-0	<2	<2
19	Hexane (n-)	110-54-3	<2	<2

Test Report

Report No.: 230410119GZU-003

Report Date: 2023-05-24

No.	Compound Name	CAS No.	Chamber Concentration $\mu\text{g}/\text{m}^3$	Emission Factor $(\mu\text{g}/\text{m}^2\cdot\text{hr})$
20	Isophorone	78-59-1	<2	<2
21	Isopropanol	67-63-0	<2	<2
22	Methyl chloroform	71-55-6	<2	<2
23	Methylene chloride	75-09-2	<2	<2
24	Methyl t-butyl ether	1634-04-4	<2	<2
25	Naphthalene	91-20-3	<2	<2
26	Phenol	108-95-2	<2	<2
27	Propylene glycol monomethyl ether	107-98-2	<2	<2
28	Styrene	100-42-5	<2	<2
29	Tetrachloroethylene	127-18-4	<2	<2
30	Toluene	108-88-3	<2	<2
31	Trichloroethylene	79-01-6	<2	<2
32	Vinyl acetate	108-05-4	<2	<2
33	Xylenes, technical mixture (m-, o-, p-xylene combined)	108-38-3	<2	<2
34		95-47-6		
35		106-42-3		

Table 4 96h non-Listed VOCs detected above lower limits of semi-quantitation.

Compound Name	CAS No.	SURROGATE ¹	CREL $(\mu\text{g}/\text{m}^3)^2$	CARB TAC ³	PROP 65 LIST ⁴	Chamber Concentration $(\mu\text{g}/\text{m}^3)$	Emission Factor $(\mu\text{g}/\text{m}^2\cdot\text{h})$
Not Detected	/	/	/	/	/	/	/

Table 5 Top Ten VOCs having the highest emission factors in 96h.

Compound Name	CAS No.	SURROGATE ¹	CREL $(\mu\text{g}/\text{m}^3)^2$	CARB TAC ³	PROP 65 LIST ⁴	Chamber Concentration $(\mu\text{g}/\text{m}^3)$	Emission Factor $(\mu\text{g}/\text{m}^2\cdot\text{h})$
Acetaldehyde#	75-07-0	/	140	√	√	3	3

Test Report

Report No.: 230410119GZU-003

Report Date: 2023-05-24

Remark:

1. Indicates which non-listed VOCs were quantified using surrogate compounds, all other compounds were quantified using pure compounds.
2. Chronic Reference Exposure Level (CREL) as defined by California Office of Environmental Health Hazard Assessment.
3. Substance is listed on California Air Resource Board's (CARB) Toxic Air Contaminant (TAC) identification list.
4. Substance known to the state of California to cause cancer or reproductive toxicity according to California's Safe Drinking Water and Toxic Enforcement Act of 1986 (Proposition 65)
5. # = indicates aldehydes identified and quantified by DNPH derivatization and HPLC/DAD analysis.
6. TVOC means sum of the concentrations of all identified and unidentified VOCs between and including n-pentane through n-heptadecane (i.e., C₅-C₁₇) as measured by the GC/MS TIC method and expressed as a toluene equivalent value.
7. Detection limit of individual compound = 1 µg/m³ for Benzene and Epichlorohydrin, 2µg/m³ for
Detection limit of TVOC = 10 µg/m³

用章
H

Test Report

Report No.: 230410119GZU-003

Report Date: 2023-05-24

Test Items, Method and Results:

7. Estimated Concentration for different scenarios and evaluation of the requirement.

Table 6 Parameters to be used for estimation of VOC concentrations

Scenario	Room Size(m ³)	Wall paint & wallcoverings exposed Surface Area (m ²)	Effective outdoor air change rate (h ⁻¹)	Air Flow Rate (m ³ /h)
Standard school classroom	231	94.6	0.82	191
Private office	30.6	33.4	0.68	20.7
Single family residence	547	562	0.23	127

Remark:

The above parameters are cited from section 01350 table 4-2, 4-3, for Standard school classroom, and table 4-4, 4-5 for Private office, and table B-1, B-2 for single family residence.

Table 7 Estimated Concentration of all Target VOCs for different scenarios and evaluation of the requirement

No.	Compound Name	CAS No.	Estimated concentration (µg/m ³)			Allowable Concentration (µg/m ³)	Verdict (Pass/Fail)		
			SC	PO	R		SC	PO	R
1	Acetaldehyde [#]	75-07-0	1.5	4.8	13.3	70	Pass	Pass	Pass
2	Benzene	71-43-2	<0.5	<1.6 [^]	<4.4 [^]	1.5	Pass	Pass	Pass
3	Carbon disulfide	75-15-0	<1.0	<3.2	<8.9	400	Pass	Pass	Pass
4	Carbon tetrachloride	56-23-5	<1.0	<3.2	<8.9	20	Pass	Pass	Pass
5	Chlorobenzene	108-90-7	<1.0	<3.2	<8.9	500	Pass	Pass	Pass
6	Chloroform	67-66-3	<1.0	<3.2	<8.9	150	Pass	Pass	Pass
7	Dichlorobenzene (1,4-)	106-46-7	<1.0	<3.2	<8.9	400	Pass	Pass	Pass
8	Dichloroethylene (1,1)	75-35-4	<1.0	<3.2	<8.9	35	Pass	Pass	Pass
9	Dimethylformamide (N,N-)	68-12-2	<1.0	<3.2	<8.9	40	Pass	Pass	Pass
10	Dioxane (1,4-)	123-91-1	<1.0	<3.2	<8.9	1500	Pass	Pass	Pass
11	Epichlorohydrin	106-89-8	<0.5	<1.6 [^]	<4.4 [^]	1.5	Pass	Pass	Pass
12	Ethylbenzene	100-41-4	<1.0	<3.2	<8.9	1000	Pass	Pass	Pass
13	Ethylene glycol	107-21-1	<1.0	<3.2	<8.9	200	Pass	Pass	Pass
14	Ethylene glycol monoethyl ether	110-80-5	<1.0	<3.2	<8.9	35	Pass	Pass	Pass
15	Ethylene glycol monoethyl ether acetate	111-15-9	<1.0	<3.2	<8.9	150	Pass	Pass	Pass
16	Ethylene glycol monomethyl ether	109-86-4	<1.0	<3.2	<8.9	30	Pass	Pass	Pass

Test Report

Report No.: 230410119GZU-003

Report Date: 2023-05-24

No.	Compound Name	CAS No.	Estimated concentration (µg/m ³)			Allowable Concentration (µg/m ³)	Verdict (Pass/Fail)		
			SC	PO	R		SC	PO	R
17	Ethylene glycol monomethyl ether acetate	110-49-6	<1.0	<3.2	<8.9	45	Pass	Pass	Pass
18	Formaldehyde [#]	50-00-0	<1.0	<3.2	<8.9	9	Pass	Pass	Pass
19	Hexane (n-)	110-54-3	<1.0	<3.2	<8.9	3500	Pass	Pass	Pass
20	Isophorone	78-59-1	<1.0	<3.2	<8.9	1000	Pass	Pass	Pass
21	Isopropanol	67-63-0	<1.0	<3.2	<8.9	3500	Pass	Pass	Pass
22	Methyl chloroform	71-55-6	<1.0	<3.2	<8.9	500	Pass	Pass	Pass
23	Methylene chloride	75-09-2	<1.0	<3.2	<8.9	200	Pass	Pass	Pass
24	Methyl t-butyl ether	1634-04-4	<1.0	<3.2	<8.9	4000	Pass	Pass	Pass
25	Naphthalene	91-20-3	<1.0	<3.2	<8.9	4.5	Pass	Pass	Pass
26	Phenol	108-95-2	<1.0	<3.2	<8.9	100	Pass	Pass	Pass
27	Propylene glycol monomethyl ether	107-98-2	<1.0	<3.2	<8.9	3500	Pass	Pass	Pass
28	Styrene	100-42-5	<1.0	<3.2	<8.9	450	Pass	Pass	Pass
29	Tetrachloroethylene	127-18-4	<1.0	<3.2	<8.9	17.5	Pass	Pass	Pass
30	Toluene	108-88-3	<1.0	<3.2	<8.9	150	Pass	Pass	Pass
31	Trichloroethylene	79-01-6	<1.0	<3.2	<8.9	300	Pass	Pass	Pass
32	Vinyl acetate	108-05-4	<1.0	<3.2	<8.9	100	Pass	Pass	Pass
33	Xylenes, technical mixture (m-, o-, p-xylene combined)	108-38-3	<1.0	<3.2	<8.9	350	Pass	Pass	Pass
34		95-47-6							
35		106-42-3							
36	TVOC	—	<5.0	<16.1	<44.3	—	—	—	—

Remark:

1. The Allowable Concentration is cited from Section 01350 table 4-1, no requirement for TVOC.
2. Individual VOC of concern is below lower limits of quantitation for modeled scenario.

Table 8 Estimated Concentration of non-listed VOCs for different scenarios

No.	Compound Name	CAS No.	Estimated concentration (µg/m ³)		
			SC	PO	R
1	Not Detected	/	/	/	/

Test Report

Report No.: 230410119GZU-003

Report Date: 2023-05-24

Appendix A: Sample Received Photo



Revision:

Revision No.	Date	REVISION	Reviser	Reviewer
/	/	Original Report Issue	/	/

*****End of Report*****